

# Allstates Coatings Co.™ PRODUCT INFORMATION

P.O. Box 1633 ● 100 Lee Street ● Gladewater, TX 75647  
903-845-6436 ● 1-800-358-3020 ● Fax: 903-845-5626

*Poly Allstates Line Paint*

MANUFACTURERS OF PAINT & COATINGS

## *Poly Allstates Line Paint*

Available Colors: ALT-603 Black Out, ALT-605 White, ALT-606 Yellow, ALT-607 Handi-Cap Blue, ALT-608 Firelane Red, ALT-609 Compact Car Green

Lead Free color are available upon request.

**GENERAL:** For exterior use on asphalt surfaces. A modified latex emulsion of superior quality that is exceptionally tough, durable, and attractive. It is ready to use on roadways, parking lots, traffic islands, walkways, aisles, fire lanes, safety areas, running tracks, play areas, tennis courts, handicap areas and all areas where caution is observed. To improve longevity of arrows and crosswalks, incorporate GB-50, Glass Beads.

### **SURFACE**

**PREPARATION:** Surface must be free from dirt and oil. It is necessary to etch concrete surface. Do not stripe when rain is forecast, when surface is wet, or when temperature is below 50°F. Contact Allstates for detailed applications.

**APPLICATION:** Mix well before using. If applied by spray, strain and dilute slightly with water if needed. For brush or roller use as is. Dries in less than thirty minutes. In shaded areas or cooler temperatures longer drying time may be required. Under normal drying conditions no traffic pick-up after 4 to 6 hours.

**COVERAGE:** 400 to 500 linear of 4" stripe per gallon      800 to 900 linear of 2" stripe per gallon  
250 to 300 linear of 6" curb per gallon

**CAUTION:** **KEEP FROM FREEZING.** Wash tools in water. Use a suitable paint thinner if material has dried. Do not store in direct sunlight. Container should be closed when not in use. Because alkali inherent in concrete surfaces there is no product guarantee on these. Keep out of the reach of children. For exterior use only.

**PACKAGING:** 1 gallon cans, 5 gallon pails, and 55 gallon drums

---

### Material Specifications:

### Requirements:

---

Weight per Gallon, ASTM D1010 (lbs) .....	10.60 - 11.00
Viscosity @ 77°F ASTM D562 (Kreb's Stormer Unit).....	75 - 85 KU
% Solids by Weight.....	48.00 ± 2.00
Scrub Resistance, cycles ASTM D248 .....	400
Flexibility, ¼" conical mandrel ASTM D .....	Pass
Fineness of grind, hegman ASTM D1210.....	2 - 4
Freeze, than stability ASTM D2243 .....	5 cycles
Volatile Organic Content (lbs/gal.).....	0.25
Flammability .....	non flammable
Shelf Life (yrs).....	1- 2

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents. Nothing herein shall constitute a warranty, express or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent implied.