

# Allstates Coatings Co.® PRODUCT INFORMATION

P.O. Box 1633 ● 100 Lee Street ● Gladewater, TX 75647  
903-845-6436 ● 1-800-358-3020 ● Fax: 903-845-5626  
www.allstatescoatings.com  
MANUFACTURERS OF PAINT & COATINGS

## Airfield Pavement Marking Paint

### Airfield Pavement Marking Paint Meets Fed. Spec. TT-P-1952B Line Paint ALT-615 White, ALT-616 Yellow

**GENERAL:** For interior and exterior use on asphaltic and concrete surfaces. A modified acrylic latex emulsion of superior quality that is exceptionally tough, durable, and attractive. Ready to use on roadways, parking lots, airfields, traffic islands, walkways, aisles, fire lanes, safety areas, athletic courts and all areas where caution is observed. The paint may be used either alone or to bind reflective beads. \*

#### SURFACE

**PREPARATION:** Surface must be free from dirt, dust and oil. It is necessary to etch concrete surface. Do not stripe when rain is forecast, on wet surface, or when temperature is below 50°F. Contact Allstates for detailed application instructions.

**APPLICATION:** Mix well before using. If applied by spray, strain and dilute slightly with water if needed. For brush or roller, use as is. Dries in less than thirty minutes. In shaded areas or cooler temperatures longer drying time may be required. No traffic pick-up after 4 to 6 hours under normal drying conditions. Drying is inhibited by moist surfaces, low temperature, high humidity, fog and dew.

**COVERAGE:** 400 to 450 linear feet of 4" stripe per gallon  
100 to 110 square feet per gallon

**CAUTION:** **KEEP FROM FREEZING.** Wash tools in water. Use a suitable paint thinner if material is dried. Do not store in direct sunlight. Container should be closed when not in use. Because of alkali inherent in concrete surfaces there is no product guarantee. For industrial use only. Keep out of reach of children.

**PACKAGING:** 5 gallon pails and 55 gallon drums.

---

#### Material Specifications:

#### Requirements:

Weight per Gallon @ 77°F, ASTM D1010, (lbs) .....	11.50 min.
% Solids by Weight, ASTM D2369 .....	50 min.
Consistency, ASTM D62 (Krebs Stormer Unit).....	70 - 90
Drying Time, minutes.....	75 max.
Bleeding Ratio .....	0.95 min
Scrub Resistance, cycles ASTM D2486 .....	400 min.

- Glass beads meeting Federal Specifications TT-B-1325B (GSA-FSS Type III, Gradation A) as amended. Federal Specifications beads; Retroreflective, glass spheres.