

P.O. Box 1633 • 100 Lee Street • Gladewater, TX 75647
 903-845-6436 • 1-800-358-3020 • Fax: 903-845-5626

**Insta - Dri® Waterborne
 Acrylic Traffic Paint**

MANUFACTURERS OF PAINT & COATINGS

Insta-Dri® Waterborne Acrylic Traffic Paint

Available Colors: ALT-635 White, ALT-636 Yellow LF, ALT-637 Handicap Blue,
 ALT-638 Firelane Red and ALT-639 Black Out

GENERAL: Insta-Dri® waterborne striping paints formulated with 100% acrylic polymer emulsions of superior quality that is exceptionally tough durable, and attractive. It is ready to use on parking lots, traffic islands, walkways, aisles, fire lanes, safety areas, and related surfaces such as roadways and highways. Rapid drying - able to stripe in early spring and late fall or at night.

SURFACE

PREPARATION: Surface must be clean-free from dirt and oil. It is necessary to etch concrete surface. Do not stripe when rain is in forecast, on wet surface, or when temperature is below 45°F.

APPLICATION: Mix well before using. If applied by spray, strain. For brush or roller use as is. Lower the temperature and higher the humidity, longer drying time may be required. It can be reflectorized by using the drop-on type Glass Beads.

COVERAGE: 400 to 450 linear feet of 4" stripe per gallon. (@ 12.0 mil. wet film).

CAUTION: **KEEP FROM FREEZING.** Wash tools in water. Use a suitable paint thinner if material has dried. Do not store in direct sunlight. Container should be closed when not in use. Because of alkali inherent in concrete surfaces there is no product guarantee on these. Keep out of the reach of children.

PACKAGING: 5 gallon pails, 55 gallon drums and 250 gallon totes.

Material Specifications:	Requirements:
Weight per Gallon @ 77°F, ASTM D1010, (lbs).....	13.30 – 14.00 lbs.
Viscosity - KU @ 77°	75 - 90 for ambient application
.....	85 -100 for heat application
% Weight solids	77.00 ± 2.00
% Vol. solids.....	58.00 ± 2.00
Dry Time (10 mil. - wet)	
@ 70F & 57% R.H. Dry through - minutes.....	5-10 min.
Dry to no pick-up minutes	2 - 4 min.
VOC, lbs/gal.....	0.40

* Can be heated to 110°F to 130°F to accelerate curing time therefore allowing the work area to be back in service sooner due to quick drying when specification require.

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents. Nothing herein shall constitute a warranty, express or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent implied.