

# Allstates Coatings Co.® PRODUCT INFORMATION

P.O. Box 1633 ● 100 Lee Street ● Gladewater, TX 75647  
 903-845-6436 ● 1-800-358-3020 ● Fax: 903-845-5626  
 www.allstatescoatings.com  
 MANUFACTURERS OF PAINT & COATINGS

**ALT - 644**  
**Insta-Dri® Sealing Additive**

## ALT - 644 Insta-Dri® Sealing Additive For Coal Tar and Asphalt Emulsion Sealers

USER friendly, complies with all V.O.C. emissions and E.P.A. standards.

**GENERAL:** Insta-Dri® Sealing Additive is a specially blended copolymer emulsion containing fast drying chemicals which modify coal tar and asphalt emulsion sealers to achieve:

- ★ 60% faster curing time
- ★ Power steering marks and tracking reduction
- ★ Outstanding toughness and adhesion
- ★ Better suspension of the aggregates
- ★ Deeper jet black color
- ★ Resistance to oils, fuels, grease and chemicals
- ★ Cost savings versus other additives

It is recommended for faster curing of asphalt sealer and power steering marking and tracking reduction. When specifications demand traffic be opened up quickly, use Insta-Dri® Sealing Additive on any asphaltic surfaces such as commercial and industrial parking lots, traffic safety islands, driveways and service stations.

**SURFACE**

**PREPARATION:** Surface must be free from dirt, dust and oil. Treat oil, grease and gasoline spots with Allstates' Poly Oil Sil® (ALT- 602).

**APPLICATION:** Mix well before using. Use 2 to 4 gallons of Insta-Dri® Sealing Additive undiluted to modify 100 gallons of sealer. The amount will vary and depend upon the type of end use in the traffic pattern areas or specifications. However we recommend 2 gallons of Insta-Dri® Sealing Additive to modify 100 gallons of sealer for a normal application. Always pour sealer first into mechanical spray or squeegee type machine, then add proper amount of water. When agitating, add Insta-Dri® Sealing Additive slowly and mix to uniform consistency. Then add proper amount of aggregates (silica sand, black beauty or any other specified aggregates) and mix thoroughly before application.

**COVERAGE:**

RECOMMENDED MIX DESIGN FORMULATION

<u>Sealer (RP 355E) Gallons</u>	<u>Water Gallons</u>	<u>Sand Pounds</u>	<u>Insta-Dri® Sealing Additive Gallons</u>
100	20-35	300-500	2 to 4

**CAUTION:** **KEEP FROM FREEZING.** Wash tools in water. Use a suitable paint thinner if material has dried. Do not store in direct sunlight. Container should be closed when not in use. Keep out of the reach of children.

**PACKAGING:** 5 gallon pails, 55 gallon drums and 275 gallon tote tanks.

Material Specifications:

Requirements:

Weight per Gallon, ASTM D1010, (lbs) .....	8.40 - 8.60
Nonvolatile %, ASTM D2939 .....	25.00 ± 3.00
Viscosity @ 77°F, ASTM D562 (Kreb's Stormer Unit) .....	50 - 60
Flammability .....	Non-flammable
PH .....	4 to 6

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents. Nothing herein shall constitute a warranty, express or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent implied. 12/8/05