

Allstates Coatings Co.[®] PRODUCT INFORMATION

100 N. Lee Drive • Gladewater, TX 75647
903-845-6436 • 1-800-358-3020 • Fax: 903-845-5626

Poly Allstates Line Paint

MANUFACTURERS OF PAINT & COATINGS

Poly Allstates Line Paint

Available Colors: ALT-509 Black Out, ALT-505 White, ALT-506 Yellow,
ALT-507 Handi-Cap Blue, ALT-508 Firelane Red

GENERAL: For exterior use on asphalt surfaces. A modified latex emulsion of superior quality that is exceptionally tough, durable, and attractive. It is ready to use on roadways, parking lots, traffic islands, walkways, aisles, fire lanes, safety areas, running tracks, play areas, tennis courts, handicap areas and all areas where caution is observed. To improve longevity of arrows and crosswalks, incorporate GB-50, Glass Beads.

SURFACE

PREPARATION: Surface must be free from dirt and oil. It is necessary to etch concrete surface. Do not stripe when rain is forecast, when surface is wet, or when temperature is below 50°F. Contact Allstates for detailed applications.

APPLICATION: Mix well before using. If applied by spray, strain and dilute slightly with water if needed. For brush or roller use as is. Dries in around thirty minutes. In shaded areas or cooler temperatures longer drying time may be required. Under normal drying conditions no traffic pick-up after 4 to 6 hours.

COVERAGE: 400 to 500 linear of 4" stripe per gallon 800 to 900 linear of 2" stripe per gallon
250 to 300 linear of 6" curb per gallon

CAUTION: **KEEP FROM FREEZING.** Wash tools in water. Use a suitable paint thinner if material has dried. Do not store in direct sunlight. Container should be closed when not in use. Because alkali inherent in concrete surfaces there is no product guarantee on these. Keep out of the reach of children. For exterior use only.

PACKAGING: 5 gallon pails, 55 gallon drums and 250 gallon totes

Material Specifications:

Requirements:

Weight per Gallon, ASTM D1010 (lbs)	10.60 - 11.00
Viscosity @ 77°F ASTM D562 (Kreb's Stormer Unit).....	75 - 85 KU
% Solids by Weight.....	58.00 ± 2.00
Scrub Resistance, cycles ASTM D248	400
Flexibility, ¼" conical mandrel ASTM D	Pass
Fineness of grind, hegman ASTM D1210.....	2 - 4
Freeze, than stability ASTM D2243	5 cycles
Volatile Organic Content (lbs/gal.).....	0.25
Flammability	non flammable
Shelf Life (yrs).....	1- 2

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents. Nothing herein shall constitute a warranty, express or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent implied.