

Allstates Coatings Co.[®] PRODUCT INFORMATION

100 N. Lee Drive ● Gladewater, TX 75647
903-845-6436 ● 1-800-358-3020 ● Fax: 903-845-5626
www.allstatescoatings.com
MANUFACTURERS OF PAINT & COATINGS

ALT-619 Oil Seal Primer

ALT-619 Oil Seal Primer (Ready to Use)

USER friendly, complies with all V.O.C. emissions and E.P.A. standards.

GENERAL: Oil Seal Primer is a modified latex emulsion formulated with suitable additives to seal and promote adhesion over oil, grease and gasoline spots, prior to the application of coal tar and asphalt sealer on asphaltic surfaces. It is ready to use on driveways, parking lots, airport runways, traffic safety islands or any asphalt surface.

SURFACE

PREPARATION: Surface must be dry, clean and free from all loose material, dirt and dust. Scrape excessive build-up of oil, grease, and dirt.

APPLICATION: Shake well before using. Oil Seal Primer is **READY TO USE**. Do not use until temperature is 50°F and rising. Apply with a stiff, bristly brush in a scrubbing motion on oil or grease. While Oil Seal Primer is wet, sprinkle a slight amount of silica sand to improve adhesion of coal tar or emulsion type sealer. Allow to dry completely. Then apply coal tar or asphalt emulsion type pavement sealer.

COVERAGE: Up to 150 to 200 square feet per gallon.

CLEAN UP: Wash thoroughly with soap and water.

CAUTION: **KEEP FROM FREEZING.** Keep out of the reach of children. Container should be closed when not in use. Oil Seal Primer is to be used on asphalt surface where asphalt has not been destroyed by heavy deposits of oil, grease, or any other chemical product. Wash tools in water.

PACKAGING: 5 gallon pails and 55 gallon drums.

Material Specifications:

Requirements:

Weight per Gallon, ASTM D1010, (lbs)	8.40 - 8.60
Viscosity @ 77°F ASTM D562 (Kreb's Stormer Unit).....	75 - 80 KU
Drying Time (min)	20 - 40
Application Temp (°F).....	50 min.
Film forming tester over oil	Film must form over oily surfaces
Flammability	non flammable
VOC Requirements.....	0.55 lbs/gal