

Allstates Coatings Co.® PRODUCT INFORMATION

100 N. Lee Drive ● Gladewater, TX 75647
 903-845-6436 ● 1-800-358-3020 ● Fax: 903-845-5626
 www.allstatescoatings.com
 MANUFACTURERS OF PAINT & COATINGS

ALT - 657 Insta-Dri® Cracksealer

ALT - 657 Insta-Dri® Rapid Cure Cracksealer HISOLIDS Cold Pour Crack Sealer (Exterior Use Only)

USER friendly complies with all V.O.C. emissions and E.P.A. standards.

GENERAL: Allstates Coatings Company Insta-Dri® Rapid Cure Cracksealer is an acrylic and ceramic modified rubberized asphalt emulsion that cures rapidly. Insta-Dri® cures up to 3 times faster than other cold pour cracksealers. It provides less shrinkage with up to twice the solids of some cracksealers and yet remains flexible even in the harshest environments. Designed for sealing narrow pavement cracks up to 1" in width in asphalt and concrete surfaces. It is ready to use on roadways, highways, streets, parking lots, airports, athletic courts, driveways, traffic safety islands, playgrounds and walkways.

- ★ Low and high temperature durability with excellent elasticity
- ★ Super high performance drying
- ★ Restricts moisture from entering the subgrade
- ★ No high temperature tracking or melting, reduced shrinkage

SURFACE

PREPARATION: Surface must be dry and free from all loose material, dirt and dust. Oil contaminated cracks can be treated with Allstates' Poly Oil Sil® (ALT - 602) to improve adhesion.

APPLICATION: Mix well before using. Use as is. Fill cracks completely. May be applied with a pour pot or suitable crack sealing machine. Before it sets up, scrape excess from surfaces using a V shape rubber squeegee. To promote adhesion to coal tar or asphalt emulsion type pavement sealer, sprinkle silica sand (lightly) before it sets up. Will set under good conditions in about an hour depending upon weather and filler thickness.

COVERAGE: Indefinite. For estimation purposes, up to 80 - 100 linear feet of ½" X ½" depth cracks.

CAUTION: **KEEP FROM FREEZING.** Do not use when rain is in forecast, when surface is wet or when temperature is below 50°F. Wash tools in water. Use a paint thinner if material has dried. Do not store in direct sunlight or where temperatures exceed 100°F. Container should be closed when not in use. Keep out of the reach of children.

PACKAGING: 1 gallon jugs, 5 gallon pails and 55 gallon drums.

Material Specifications:

Requirements:

Weight per Gallon @ 77°F, ASTM D1010 (lbs).....	10.80 – 11.00
Nonvolatile %, ASTM D2939.....	76.00 – 80.00
Viscosity @ 77°F, ASTM D562 (Kreb's Stormer Unit).....	90 - 120
Elongation %, ASTM D412.....	1000
% Recovery (after elongation) ASTM D412 min.....	70
Penetration (0.1 mm), ASTM D5.....	45
Application Temp. (°F).....	50 min.
Ductility, 5 cm/min. @ 25°C (77°F) & 4°C (39.2°F).....	120+ cm.
Softening Point (°F), ASTM D36.....	160
Std. Spec. for Emulsified Asphalt	
AASHTO Designation M140 – 70.....	meets spec.
ASTM Designation D977 – 73 & D244	meets spec.

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents. Nothing herein shall constitute a warranty, express or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent implied. 12/8/05