

# Allstates Coatings Co.® PRODUCT INFORMATION

100 N. Lee Drive ● Gladewater, TX 75647  
 903-845-6436 ● 1-800-358-3020 ● Fax: 903-845-5626  
 www.allstatescoatings.com  
 MANUFACTURERS OF PAINT & COATINGS

ALT-662 Ro-Flex™

## ALT-662 Ro-Flex™

### Aqua Seal - Super Sealant

USER friendly, complies with all V.O.C. emissions and E.P.A. standards.

**GENERAL:** Ro-Flex™ Aqua Seal is used in any Portland Cement or Asphalt Cement water conveyance system, bridge or road embankments with 60° or less side slope. Ro-Flex™ Aqua Seal Super Sealant joint sealer is a high performance, cold pour rubber concrete or asphalt crack and joint sealer that combines strong adhesive properties with high elasticity. They provide a durable seal during expansion and contraction, and an extra measure of bond during cold weather. Resistant to flow at high temperatures in exposed areas. Cured dried film meets the characteristics and performance of the commonly used joint sealant but is environmentally friendly.

### APPLICATION INSTRUCTIONS:

- Clean and prepare joint by removing dust, dirt and other foreign debris, and if necessary the old joint sealant.
- Apply joint sealant flush to the surface of the pavement. Both air and pavement temperature should be 50°F and rising.
- Can be heated to accelerate curing time in low temperature and / or high humidity.
- Use Allstates' Crac Shot Retrofit Pump System for larger applications.

**COVERAGE:** Indefinite. For estimation purposes - up to 80 linear feet of ½" X ½" depth cracks.

**CAUTION:** **KEEP FROM FREEZING. Do not use when rain or freezing is in forecast, when surface is wet or when temperature is below 45°F.** Wash tools in water, use paint thinner if material has dried. Container should be closed when not in use. Do not store in direct sunlight or where temperatures exceed 100°F. Keep out of the reach of children

**PACKAGING:** 5 gallon pails and 55 gallon drums.

#### Material Specifications:

#### Requirements:

Weight per Gallon @ 77°F, ASTM D1010, (lbs).....	9.20 - 9.40
Nonvolatile %, ASTM D2939 .....	66.00 - 70.00
Viscosity @ 77°F, ASTM D562 (Kreb's Stormer Unit).....	100 - 120
Softening Point (0°F), ASTM D36 .....	160
Penetration (0.1 mm), ASTM D5 .....	35 min.
Elongation %, ASM D412 .....	100
Std. Spec. for Emulsified Asphalt	
AASHTO Designation M 140-70 .....	meets spec.
ASTM Designation D997-69 & D244 .....	meets spec.
Flammability .....	non flammable