



## ALT - 644 Insta-Dri® Sealing Additive

### For Coal Tar and Asphalt Emulsion Sealers

USER friendly, complies with all V.O.C. emissions and E.P.A. standards.

**GENERAL:** Insta-Dri® Sealing Additive is a specially blended copolymer emulsion containing fast drying chemicals which modify refined coal tar and asphalt emulsion sealers to achieve:

- ★ 50% faster curing time
- ★ Power steering marks and tracking reduction
- ★ Outstanding toughness and adhesion
- ★ Better suspension of the aggregates
- ★ Deeper jet black color
- ★ Resistance to oils, fuels, grease and chemicals
- ★ Cost savings versus other additives

When specifications demand traffic be opened up quickly, use Insta-Dri® Sealing Additive on any asphaltic surfaces such as commercial and industrial parking lots, traffic safety islands, driveways and service stations.

#### SURFACE

**PREPARATION:** Surface must be free from dirt, dust and oil. Treat oil, grease and gasoline spots with Allstates' Poly Oil Sil® (ALT- 602).

**APPLICATION:** Mix well before using. Use 2 to 4 gallons of Insta-Dri® Sealing Additive undiluted to modify 100 gallons of sealer. The amount will vary and depend upon the type of end use in the traffic pattern areas or specifications. However we recommend 2 gallons of Insta-Dri® Sealing Additive to modify 100 gallons of sealer for a normal application. Always pour sealer first into mechanical spray or squeegee type machine, then add proper amount of water. When agitating, add Insta-Dri® Sealing Additive slowly and mix to uniform consistency. Then add proper amount of aggregates (silica sand, black beauty or any other specified aggregates) and mix thoroughly before application.

#### COVERAGE:

##### RECOMMENDED MIX DESIGN FORMULATION

<u>Sealer (RP 355E) Gallons</u>	<u>Water Gallons</u>	<u>Sand Pounds</u>	<u>Insta-Dri® Sealing Additive Gallons</u>
100	20-35	300-500	2 to 4

**CAUTION:** **KEEP FROM FREEZING.** Wash tools in water. Use a suitable paint thinner if material has dried. Do not store in direct sunlight. Container should be closed when not in use. Keep out of the reach of children.

**PACKAGING:** 5 gallon pails, 55 gallon drums and 275 gallon tote tanks.

#### Material Specifications:

#### Requirements:

Weight per Gallon, ASTM D1010, (lbs) .....	8.25 - 8.50
Nonvolatile %, ASTM D2939 .....	21.00 ± 3.00
Viscosity @ 77°F, ASTM D562 (Kreb's Stormer Unit) .....	60 - 75
Flammability .....	Non-flammable
PH .....	4 to 6